What is claimed is:

5

- 1. A surface tension control agent for coating materials comprising:
- a fluorine-containing (meth)acryl type copolymer obtained by copolymerization of monomers comprising
 - a fluorine-substituted alkyl (meth)acrylate monomer (A);
 - an alkyl (meth)acrylate monomer (B); and
- a hydroxyl group- or ether group-containing alkyl (meth)acrylate monomer (C),
- wherein the ratio of (A) to {(B)+(C)} in the copolymer is in the range of 3-60 parts by weight to 40-97 parts by weight.
 - 2. The surface tension control agent according to Claim 1, wherein the fluorine-containing (meth)acryl type copolymer is a copolymer obtained by copolymerization of monomers comprising:

the monomer (A);

the monomer (B);

the monomer (C); and

- at least one kind of vinyl monomer (D) selected from the group 20 consisting of styrene, alkyl vinyl ether, alpha-olefin and maleic anhydride.
 - 3. The surface tension control agent according to Claim 1, wherein a weight-average molecular weight of the fluorine-containing (meth)acrylate copolymer is in the range of 1,500-300,000.

25

15

4. The surface tension control agent according to Claim 1, wherein

the monomer (A) is an alkyl (meth)acrylate having a perfluoro alkyl group with 2-18 carbon atoms.

- 5. The surface tension control agent according to Claim 1, wherein the monomer (B) is an alkyl (meth)acrylate having an alkyl group with 1-30 carbon atoms.
- 6. The surface tension control agent according to Claim 1, wherein the monomer (C) is at least one kind of a hydroxyl group- or ether group-containing alkyl (meth)acrylate represented by the following formula (1)

$$CH_2 = C(R^1) - CO - O - A$$
 (1)

(where R1 is hydrogen atom or methyl group; -A is a hydroxyl alkyl group with 2-4 carbon atoms or an alkyl substituent thereof, an alkyl monoalkylene glycol group having an alkyl group with 1-18 carbon atoms, an alkyl polyalkylene glycol group having an alkyl group with 1-18 carbon atoms, an alkenyl monoalkylene glycol group having an alkenyl group with 2-18 carbon atoms, or an alkenyl group-substituted polyalkylene glycol group having an alkenyl group with 2-18 carbon atoms).

20

5

10

15

7. A coating material comprising:

a surface tension control agent for coating materials, which comprises a fluorine-containing (meth)acryl type copolymer obtained by copolymerization of monomers comprising

a fluorine-substituted alkyl (meth)acrylate monomer (A); an alkyl (meth)acrylate monomer (B); and a hydroxyl group- or ether group-containing alkyl (meth)acrylate monomer (C),

wherein the ratio of (A) to $\{(B)+(C)\}$ in the copolymer is in the range of 3-60 parts by weight to 40-97 parts by weight.

5

8. The coating material according to Claim 7, wherein the fluorine-containing (meth)acrylate type copolymer is a copolymer obtained by copolymerization of monomers comprising:

the monomer (A);

10 the monomer (B);

the monomer (C); and

at least one kind of vinyl monomer (D) selected from the group consisting of styrene, alkyl vinyl ether, alpha-olefin and maleic anhydride.

- 9. The coating material according to Claim 7, wherein the weight-average molecular weight of the fluorine-containing (meth)acryl type copolymer is in the range of 1,500-300,000.
- 10. The coating material according to Claim 7, wherein the monomer 20 (A) is an alkyl (meth)acrylate having a perfluoroalkyl group with 2-18 carbon atoms.
- 11. The coating material according to Claim 7, wherein the monomer (B) is an alkyl (meth)acrylate having an alkyl group with 1-30 carbon atoms.

12. The coating material according to Claim 7, wherein the monomer (C) is at least one kind of hydroxyl group- or ether group-containing alkyl (meth)acrylate represented by the following formula (1)

$$CH_2 = C(R^1) - CO - O - A$$
 (1)

- (where R¹ is hydrogen atom or methyl group; -A is a hydroxy alkyl group with 2-4 carbon atoms or an alkyl substituent thereof, an alkyl monoalkylene glycol group having an alkyl group with 1-18 carbon atoms, an alkyl polyalkylene glycol group having an alkyl group with 1-18 carbon atoms, an alkenyl monoalkylene glycol group having an alkenyl group with 2-18 carbon atoms, or an alkenyl group-substituted polyalkylene glycol group having an alkenyl group with 2-18 carbon atoms).
 - 13. The coating material according to Claim 7, wherein the coating material further comprises an acrylic resin.